

Optical Compensation Medium Properties



Lot Number	Prepared on	Parameter	Value
1121-E	2011-02-28	Mua WL1	0.0039
		Mua WL2	0.0045
		Mua WL3	0.0040
		Mua WL4	0.0046
		Mus WL1	1.14
		Mus WL2	1.06
		Mus WL3	0.98
		Mus WL4	0.88
1111-E	2011-01-24	Mua WL1	0.0040
		Mua WL2	0.0047
		Mua WL3	0.0042
		Mua WL4	0.0048
		Mus WL1	1.16
		Mus WL2	1.09
		Mus WL3	0.98
		Mus WL4	0.88
10Y1-E	2010-11-29	Mua WL1	0.0040
		Mua WL2	0.0046
		Mua WL3	0.0041
		Mua WL4	0.0047
		Mus WL1	1.18
		Mus WL2	1.10
		Mus WL3	1.01
		Mus WL4	0.90
10X1-E	2010-10-05	Mua WL1	0.0041
		Mua WL2	0.0046
		Mua WL3	0.0041
		Mua WL4	0.0047
		Mus WL1	1.13
		Mus WL2	1.04
		Mus WL3	0.96
		Mus WL4	0.87
1081-E	2010-08-10	Mua WL1	0.0040
		Mua WL2	0.0047
		Mua WL3	0.0041
		Mua WL4	0.0038
		Mus WL1	1.12
		Mus WL2	1.04
		Mus WL3	0.95
		Mus WL4	0.88

Optical Compensation Medium Properties



Lot Number	Prepared on	Parameter	Value
1061-E	2010-06-21	Mua WL1	0.0041
		Mua WL2	0.0046
		Mua WL3	0.0041
		Mua WL4	0.0047
		Mus WL1	1.13
		Mus WL2	1.05
		Mus WL3	0.96
		Mus WL4	0.87
1031ext	2010.03.23	Mua WL1	0.0034
		Mua WL2	0.0041
		Mua WL3	0.0037
		Mua WL4	0.0045
		Mus WL1	1.07
		Mus WL2	0.95
		Mus WL3	0.89
		Mus WL4	0.81
1031	2010.03.23	Mua WL1	0.0037
		Mua WL2	0.0042
		Mua WL3	0.0038
		Mua WL4	0.0044
		Mus WL1	1.12
		Mus WL2	1.00
		Mus WL3	0.93
		Mus WL4	0.85
1011	2010.01.26	Mua WL1	0.0037
		Mua WL2	0.0042
		Mua WL3	0.0039
		Mua WL4	0.0044
		Mus WL1	1.12
		Mus WL2	1.02
		Mus WL3	0.95
		Mus WL4	0.85
09Y1-E	2009.11.02	Mua WL1	0.0038
		Mua WL2	0.0043
		Mua WL3	0.0039
		Mua WL4	0.0044
		Mus WL1	1.13
		Mus WL2	1.05
		Mus WL3	0.98
		Mus WL4	0.87

Optical Compensation Medium Properties



Lot Number	Prepared on	Parameter	Value
0981-E	2009.08.19	Mua WL1	0.0038
		Mua WL2	0.0043
		Mua WL3	0.0039
		Mua WL4	0.0044
		Mus WL1	1.14
		Mus WL2	1.05
		Mus WL3	0.99
		Mus WL4	0.87
0961-E	2009.06.22	Mua WL1	0.0039
		Mua WL2	0.0044
		Mua WL3	0.0040
		Mua WL4	0.0045
		Mus WL1	1.12
		Mus WL2	1.03
		Mus WL3	0.95
		Mus WL4	0.85
0942-E	2009.04.20	Mua WL1	0.0039
		Mua WL2	0.0045
		Mua WL3	0.0040
		Mua WL4	0.0045
		Mus WL1	1.15
		Mus WL2	1.07
		Mus WL3	0.99
		Mus WL4	0.88
0941-E	2009.02.11	Mua WL1	0.0038
		Mua WL2	0.0045
		Mua WL3	0.0040
		Mua WL4	0.0046
		Mus WL1	1.14
		Mus WL2	1.06
		Mus WL3	0.97
		Mus WL4	0.87
08Y1-E	2008.11.20	Mua WL1	0.0041
		Mua WL2	0.0046
		Mua WL3	0.0041
		Mua WL4	0.0048
		Mus WL1	1.16
		Mus WL2	1.05
		Mus WL3	0.97
		Mus WL4	0.90

Optical Compensation Medium Properties



Lot Number	Prepared on	Parameter	Value
0891-E	2008.09.18	Mua WL1	0.0042
		Mua WL2	0.0047
		Mua WL3	0.0041
		Mua WL4	0.0048
		Mus WL1	1.16
		Mus WL2	1.04
		Mus WL3	0.96
		Mus WL4	0.88